

Effects of Porosity on Mechanical Properties of Zirconium Oxide/AA1100 Alloy Metal Matrix Composites

¹S. Madhav Reddy and A. Chennakesava Reddy²

¹Research Scholar, Department of Mechanical Engineering, Osmania University, Hyderabad, India

²Professor, Department of Mechanical Engineering, JNT University, Hyderabad, India
dr_acreddy@yahoo.com

Abstract: In the present work, the ZrO_2 /AA1100 alloy metal matrix composites were analyzed for micromechanical properties in the presence of porosity. The results obtained from the finite element analysis of ZrO_2 /AA1100 alloy composites were in agreement with the experimental result. The tensile strength and elastic modulus have decreased with the presence of porosity in ZrO_2 /AA1100 alloy composites.

Keywords: Zirconium oxide, AA1100 alloy, unit cell models, finite element analysis, porosity.

1. INTRODUCTION

Defects can inadvertently be produced in composite materials during the manufacturing process. The most common defect is porosity. The porosity may be in the form of small voids in the matrix. Porosity levels can be critical, as they affect mechanical properties of the metal matrix composites [1-6]. From previous reviews, among the causes of porosity formation are air bubbles entering the melt matrix material, water vapor on the particles surfaces, gas entrapment during mixing process, evolution of hydrogen, and shrinkage during solidification. Stir casting method is a relatively low cost liquid processing present to produce MMC and hence, this processing technique had been utilized in this study [7-20]. Moreover, this type of processing is now in commercial use for particulate Al-based composites [21-30] and the material produced is suitable for further operations, such as pressure die-casting [30-39].

The current work presents the effect of porosity, volume fraction of particles and distribution of particles on micromechanical behavior of zirconium oxide/AA1100 metal matrix composites. The shape of zirconium oxide (ZrO_2) nanoparticle considered in this work is spherical. Finite element analysis was used to analyze unit cells with and without porosity.




Figure 1: Stir casting process; cold rolling (b); shape and dimensions of tensile specimen (c); and tensile testing on UTM (d).

2. MATERIALS METHODS

The matrix material was AA1100 alloy. The reinforcement material was ZrO₂ nanoparticles of average size 100nm. ZrO₂/AA1100 alloy composites were fabricated by the stir casting process and low pressure casting technique with argon gas at 3.0 bar. The composite samples were given solution treatment and cold rolled to the predefined size of tensile specimens. The heat-treated samples were machined to get flat-rectangular specimens (figure 1) for the tensile tests. The tensile specimens were placed in the grips of a Universal Test Machine (UTM) at a specified grip separation and pulled until failure. The test speed was 2 mm/min. A strain gauge was used to determine elongation. In the current work, a unit cell comprising of nine particles was implemented to analyze the tensile behavior ZrO₂/AA1100 composites at three (10%, 20% and 30%) volume fractions of ZrO₂. The large strain PLANE183 element was used in the matrix in all the models. In order to model the adhesion between the matrix and the particle, a CONTACT 172 element was used with reference to application of finite element method for several metal matrix composites. The finite element analysis was carried out on a unit cell without porosity as shown in figure 2a and with porosity as shown in figure 2b.




Figure 2: Unit cells: (a) without porosity and (b) with porosity.

Density of the composite is calculated from ‘Rule of Mixture’ as follows:

$$\left(\frac{v_p}{\rho_p} + \frac{1-v_p}{\rho_m}\right) \leq \rho_c \leq (1-v_p)\rho_m \quad (1)$$

where v_p is the volume fraction of particles and ρ_c , ρ_p , and ρ_m are densities of composite, particles and matrix, respectively.

Considering adhesion, formation of precipitates, particle size, agglomeration, voids/porosity, obstacles to the dislocation, and the interfacial reaction of the particle/matrix, the formula for the strength of composite is stated below:

$$\sigma_c = \left[\sigma_m \left\{ \frac{1-(v_p-v_v)^{2/3}}{1-1.5(v_p-v_v)} \right\} \right] e^{m_p(v_p-v_v)} + k d_p^{-1/2} \quad (2)$$

$$k = E_m m_m / E_p m_p$$

where, v_v and v_p are the volume fractions of voids/porosity and nanoparticles in the composite respectively, m_p and m_m are the poisson’s ratios of the nanoparticles and matrix respectively, d_p is the mean nanoparticle size (diameter) and E_m and E_p are elastic moduli of the matrix and the particle respectively. Elastic modulus (Young’s modulus) is a measure of the stiffness of a material and is a quantity used to characterize materials. Elastic modulus is the same in all orientations for isotropic materials. Anisotropy can be seen in many composites.

The upper-bound equation is given by

$$\frac{E_c}{E_m} = \left(\frac{1-v_v^{2/3}}{1-v_v^{2/3}+v_v} \right) + \frac{1+(\delta-1)v_p^{2/3}}{1+(\delta-1)(v_p^{2/3}-v_p)} \quad (3)$$

The lower-bound equation is given by

$$\frac{E_c}{E_m} = 1 + \frac{v_p-v_p}{\delta/(\delta-1)-(v_p+v_v)^{1/3}} \quad (4)$$

where, $\delta = E_p/E_m$.

3. RESULTS AND DISCUSSION

Figure 3a shows the variation of normalized tensile strengths of the composites with volume fractions of ZrO₂ particles. Adding ZrO₂ particles to AA1100 alloy matrix increased tensile strength without porosity ZrO₂/AA1100 composites. Due to the effect of porosity in ZrO₂/AA1100 composites, the tensile strength decreased; but it increased with increase of ZrO₂ content in

AA1100 alloy matrix. The tensile stresses obtained from the finite element analysis (FEA) were higher than those obtained from the mathematical expression mentioned in Eq.(2) and the experimental procedure as shown in figure 3a. This is owing to the ignorance of clustering of ZrO_2 particles in AA1100 alloy matrix.




Figure 3: Effect of volume fraction on (a) normalized strength, (b) normalized tensile elastic modulus, (c) normalized shear modulus and (d) density of $ZrO_2/AA1100$ composites.




Figure 4: Microstructure showing distribution of 10%, 20% and 30% ZrO_2 nanoparticles in AA1100 alloy matrix.

The normalized elastic modulus increased with increase of volume fraction of ZrO_2 particles in AA1100 alloy matrix without porosity in the composites; while it decreased with increase of volume fraction of clustered ZrO_2 particles in AA1100 alloy matrix with porosity (figure 3b). The normalized shear modulus is constant with increase of volume fraction of ZrO_2 with and without porosity (figure 3c). The porosity in various composites is shown in figure 3d. The porosity level increased with increase of volume fraction of ZrO_2 in AA1100 alloy matrix as shown in figure 4d. This is confirmed with the microstructures of the composites shown in figure 4.

In all the models (figure 5), the amount of porosity was maintained constant. Without porosity in the composites, the induced stress increased with increase of volume fraction of ZrO_2 in AA1100 alloy matrix. With porosity in the composite, the induced stress was high. This indicates that the stress exceeds the allowable stress in the composites with porosity for the same load as that applied on the composites without porosity. This is attributed to the fact of the stress concentration in the vicinity of the porosity. However, the stress decreased with increase of volume fraction ZrO_2 . This trend is in agreement with the results obtained from experimental procedure and mathematical computation.




Figure 5: Images of tensile stresses obtained from FEA: (a) without porosity and (b) with porosity.

4. CONCLUSIONS

The porosity has been increased with increase of ZrO₂ particles in AA1100 alloy matrix. In the presence of porosity, the stresses developed in the composites have exceeded the allowable stress for the same load applied on all the composite specimens. The stress concentrations were observed in the regions of porosity in the composites. The elastic modulus decreased with porosity in the composites.

REFERENCES

1. M. M. Schwartz, *Composite Materials: Processing, Fabrication and Application*, USA: Prentice Hall, 1977.
2. M. Chamundeswari and A. C. Reddy, Evaluation of strength improvement in tempered AA5050/SiC metal matrix composites using finite element analysis: experimental validation, National Conference on Advances in Design Approaches and Production Technologies (ADAPT-2005), Hyderabad, 22-23rd August 2005, pp. 338-340.
3. S. Sujatha and A. C. Reddy, Assessment of strength improvement in heat treated AA2024/SiC metal matrix composites using finite element analysis: experimental validation, National Conference on Advances in Design Approaches and Production Technologies (ADAPT-2005), Hyderabad, 22-23rd August 2005, pp. 341-343.
4. M. Skibo, P. L. Morris, D. J. Lloyd, Structure and Properties of Liquid Metal Processed SiC Reinforced Aluminium: Cast Reinforced Metal Composites. In: Fishman, S.G., and Dhingra, A.K. (eds.). *World Materials Congress*, 1988, pp. 257-261.
5. B. Ramana A. C. Reddy, and S. Somi Reddy, Fracture analysis of mg-alloy metal matrix composites, National Conference on Computer Applications in mechanical Engineering, Anantapur, 21st December 2005, pp.57-61.
6. A. Chennakesava Reddy and B. Kotiveerachari, Effect of Matrix Microstructure and Reinforcement Fracture on the Properties of Tempered SiC/Al-Alloy Composites, National conference on advances in materials and their processing, Bagalkot, 28-29th November, 2003, pp.78-81.
7. W. R. Hoover, Die-Casting of Duralcan Composites – Processing, Microstructure and Properties. In: Hansen, N., D. J Jensen, T. Leffers, H. Lilholt, T. Lorentzen, A. S. Pedersen, O.B. Pedersen, and B. Ralph (eds.). Denmark: Risø National Laboratory, 1991, pp. 387-392.
8. A. Chennakesava Reddy, Analysis of the Relationship Between the Interface Structure and the Strength of Carbon-Aluminum Composites, NATCON-ME, Bangalore, 13-14th March 2004, pp.61-62.
9. A. Chennakesava Reddy, Studies on fracture behavior of brittle matrix and alumina trihydrate particulate composites, *Indian Journal of Engineering & Materials Sciences*, 9, 2003, pp.365-368.
10. T. W. Clyne, *Physical Metallurgy: Metallic Composite Materials*, UK: Elsevier Science, 1996.
11. S. Madhav Reddy, A. C. Reddy, Clustering in Zirconium Oxide/AA1100 Alloy Particle-Reinforced Metal Matrix Composites, 4th International Conference on Composite Materials and Characterization, Hyderabad, India, 7-8 March 2003, pp. 182-187.
12. P. Laxminarayana, A. C. Reddy, Numerical Investigation of the Effect of Particle Clustering on the Micromechanical Properties of Titanium Nitride/AA4015 Alloy Particle-Reinforced Metal Matrix Composites, 4th International Conference on Composite Materials and Characterization, Hyderabad, India, 7-8 March 2003, pp. 193-196.
13. A. Kelly, C. Zweben., T. W. Clyne, *Comprehensive Composite Materials: Volume 3 Metal Matrix Composites*. UK: Pergamon, 2000.
14. A. Chennakesava Reddy, Experimental Evaluation of Elastic Lattice Strains in the Discontinuously SiC Reinforced Al-alloy Composites, National Conference on Emerging Trends in Mechanical Engineering, Nagapur, 05-06th February, 2004, pp.81, Paper No. e-TIME/110/E-07.

15. P. Laxminarayana, A. C. Reddy, Effect of Particle Spatial Distribution and Clustering on Tensile Behavior of Titanium Oxide/AA5050 Alloy Particle Reinforced Composites, 4th International Conference on Composite Materials and Characterization, Hyderabad, India, 7-8 March 2003, pp. 197-201.
16. R. Chen, G. D. Zhang, R. J. Wu., H. Sekine, The Effect of SiC Particle and Whisker on the Strength of Aluminium Alloy Matrix Composites, *Acta Metallurgica Sinica*, 10, 1997, pp. 22-34.
17. S. Madhav Reddy, A. C. Reddy, Effect of Particle Clustering on Micromechanical Properties of Boron Nitride/AA3003 Alloy Particle-Reinforced Metal Matrix Composites, 4th International Conference on Composite Materials and Characterization, Hyderabad, India, 7-8 March 2003, pp. 188-192.
18. Essa Zitoun, A. C. Reddy, Agglomeration of Nanoparticles into Network Aggregates in Zirconium Carbide/AA6061 Alloy Particle Reinforced Composites, 4th International Conference on Composite Materials and Characterization, Hyderabad, India, 7-8 March 2003, pp. 202-205.
19. J. Zhang, The Effect of Porosity on the Microstructural Damping Response of 6061 Aluminium Alloy, *Journal Material Science*, 28, 1993, pp. 1515-1524.
20. Essa Zitoun, A. C. Reddy, Unit Cell Models for Clustering of Particles embedded in MgO Particle/AA8090 Alloy Metal Matrix Composites, 4th International Conference on Composite Materials and Characterization, Hyderabad, India, 7-8 March 2003, pp. 211-215.
21. A. Chennakesava Reddy, Investigation of the Clustering Behavior of Titanium Diboride Particles in TiB₂/AA2024 Alloy Metal Matrix Composites, 4th International Conference on Composite Materials and Characterization, Hyderabad, India, 7-8 March 2003, pp.216-220.
22. P. K. Ghosh, S. Ray, Effect of Porosity and Alumina Content on the High Temperature Mechanical Properties of Compocast Aluminium Alloy –Alumina Particulate Composite, *Journal of Materials Science*, 22, 1987, pp. 4077-4086.
23. A. Chennakesava Reddy, Micromechanical Modelling of Interfacial Debonding in AA1100/Graphite Nanoparticulate Reinforced Metal Matrix Composites, 2nd International Conference on Composite Materials and Characterization, Nagpur, India, 9-10 April 1999, pp. 249-253.
24. A. Chennakesava Reddy, Cohesive Zone Finite Element Analysis to Envisage Interface Debonding in AA7020/Titanium Oxide Nanoparticulate Metal Matrix Composites, 2nd International Conference on Composite Materials and Characterization, Nagpur, India, 9-10 April 1999, pp. 204-209.
25. J. Hashim, L. Looney, M. S. J. Hashmi, Metal Matrix Composites: Production by the Stir Casting Method, *Journal of Materials Processing Technology*, 92-93, 1999, pp. 1-7.
26. A. Chennakesava Reddy, Simulation of MgO/AA6061 Particulate-Reinforced Composites Taking Account of CTE Mismatch Effects and Interphase Separation, 3rd National Conference on Materials and Manufacturing Processes, Hyderabad, India, 22-25 February 2002, pp. 184-187.
27. V. K. Prasad and A. C. Reddy, Tensile behavior of tempered AA5050/Al₂O₃ metal matrix composites using RVE models: experimental validation, National Conference on Advances in Design Approaches and Production Technologies (ADAPT-2005), Hyderabad, 22-23rd August 2005, pp. 335-337.
28. S. F. Moustafa, Casting of Particulate Al-Base Composites, *Zeitschrift Fuer Metallkunde*, 88, 1997, pp.209-216.
29. A. Chennakesava Reddy, Two dimensional (2D) RVE-Based Modeling of Interphase Separation and Particle Fracture in Graphite/5050 Particle Reinforced Composites, 3rd National Conference on Materials and Manufacturing Processes, Hyderabad, India, 22-25 February 2002, pp. 179-183.
30. K. Swapna Sudha and A. C. Reddy, Tensile performance of heat treated AA2024/Al₂O₃ metal matrix composites using RVE models: experimental validation, National Conference on Advances in Design Approaches and Production Technologies (ADAPT-2005), Hyderabad, 22-23rd August 2005, pp. 332-334.
31. D. Emadi, J. E. Gruzleski, Effects of Casting and Melt Variables on Porosity in Directionally-Solidified Al-Si Alloys, *American Foundry Society Transactions*, 95, 1995, pp. 307-312.
32. A. Chennakesava Reddy, Micromechanical and fracture behaviors of Ellipsoidal Graphite Reinforced AA2024 Alloy Matrix Composites, 2nd National Conference on Materials and Manufacturing Processes, Hyderabad, India, 10-11 March 2000, pp. 96-103.
33. A. Chennakesava Reddy, Constitutive Behavior of AA5050/MgO Metal Matrix Composites with Interface Debonding: the Finite Element Method for Uniaxial Tension, 2nd National Conference on Materials and Manufacturing Processes, Hyderabad, India, 10-11 March 2000, pp. 121-127.
34. S. Ray, Casting of Composite Components. Proceeding of the 1995 Conference on Inorganic Matrix Composites, Bangalore, India, 1996. Pp. 69-89.
35. A. Chennakesava Reddy, Effect of CTE and Stiffness Mismatches on Interphase and Particle Fractures of Zirconium Carbide /AA5050 Alloy Particle-Reinforced Composites, 3rd International Conference on Composite Materials and Characterization, Chennai, India, 11-12 May 2001, pp. 257-262.
36. A. Chennakesava Reddy, Behavioral Characteristics of Graphite /AA6061 Alloy Particle-Reinforced Metal Matrix Composites, 3rd International Conference on Composite Materials and Characterization, Chennai, India, 11-12 May 2001, pp. 263-269.
37. X. G. Chen, S. Engler, Formation of Gas Porosity in Aluminium Alloys, *American Foundry Society Transactions*, 92-94, 1993, pp. 673-682.
38. B. Balu Naik, A. C. Reddy and T. K. K. Reddy, Finite element analysis of some fracture mechanisms, International Conference on Recent Advances in Material Processing Technology, Kovilpatti, 23-25th February 2005, pp.265-270.
39. A. Chennakesava Reddy, Finite Element Analysis Study of Micromechanical Clustering Characteristics of Graphite/AA7020 Alloy Particle Reinforced Composites, 4th International Conference on Composite Materials and Characterization, Hyderabad, India, 7-8 March 2003, pp. 206-210.